

# United Elchem Industries

## Pool-Tite™ PVC Cement



### MORE COMPLETED POOL JOBS = MORE REVENUE FOR YOU!

Pool-Tite cement is designed to maximize your productivity for pool installations or repairs for both wet and dry situations.

#### Set Up Time

30°F to 50°F 4-5 minutes

50°F to 70°F 3-4 minutes

70°F to 100°F 1-2 minutes

#### FAST...

Pool-Tite sets up fast

- > Sets up in just 1-2 minutes (see chart).
- > Bond strengths in excess of 250 psi in 10 minutes under lab conditions

#### EASY...

Versatile cement used in many applications

- > Recommended for use on all schedules and classes of flexible and rigid PVC pipe and fittings up to 6" with interference fit
- > No primer needed on non-pressure DWV up to 4" where local codes permit

Product Number	Size	Carton Quantity
2366S	4 oz	24
2356S	8 oz	24
2346S	16 oz	24
2336S	32 oz	12
2324	Gallon	6

System may be hydrostatically tested up to 75 PSI after 15 minutes and up to 180 PSI after 30 minutes.\*

\*At temperatures above 60°F and up to 2" pipe diameter.

United Elchem  
Industries

©2011 Oatey SCS. All Rights Reserved.  
This information is based on data believed to be reliable but Oatey makes no warranties, express or implied, as to its accuracy and assumes no liability arising out of its use. The data listed falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. Oatey's liability to purchasers is expressly limited to the terms and conditions of sale.  
Oatey is a trademark of Oatey Co. All other trademarks can be found on [www.oatey.com](http://www.oatey.com).

DISTRIBUTED BY:

**OATEYSCS®**  
Supply Chain Services

216.267.7100 / 800.321.9532  
[www.oateyscs.com](http://www.oateyscs.com)